ESTEX CHAUSSETTES TECHNIQUES – ENTREPRISE FAMILIALE FRANÇAISE	***Fiche Technique*** 12/2023	**TALUX SA** 26 rue A. Volta – ZI Nord - F-77335 MEAUX CEDEX **Tél. +33(0)1.64.35.23.01** **Port : +33(0)6.13.53.27.18** **Email emmanuel@talux.com - marjorie@talux.com**

Ref. 1.986 CHAUSSETTE NON-INFLAMMABLE

Made in Italy



TRICOT MOYEN



COLORIS : Noir

35/37	38/40	41/43	44/46	47/49
EAN 3414440006541	EAN 3414440006558	EAN 3414440006565	EAN 3414440006572	EAN 3414440006589

Composition :
50% Viscose 50% Laine Mérinos

Label(s) :

Lenzing FR® THE HEAT PROTECTION FIBER

Descriptif : Chaussette non inflammable

Tricot confort toute bouclette.
Bandes élastiques de maintien : pied et cheville.
Renfort talon et pointe.
Double bouclette intérieure.

Code douanier	6115969900
Conditions de lavage	

+ Consommateur

Chaussettes Spécial – adaptée aux risques liés au feu.
Chaussette évitant la propagation de la flamme en cas de contact accidentel avec une flamme.
ISO 15025 : 2016
Ne contient aucune substance allergène ou toxique connue à ce jour.
À stocker dans un endroit propre, sec, à l'abri de la lumière directe du soleil.
La salissure peut réduire la protection.
Aucune réparation possible.

eurofins | Softlines & Leather

Analytical Report Nr. AR-23-YL-110329-01
Date 23-Nov-2023

ANALYTICAL REPORT

Client Information

Calze Tracy Srl
Via Prampolini, 7B
Monza (ITALY)

For the attention of Mr. Alessandro

Order Information

Order Code:	EFYL23110362
Reception Date:	22-Nov-2023
Analysis Starting Date:	22-Nov-2023
Analysis Ending Date:	23-Nov-2023
Decision Rule:	Binary Statement with Guard Band. Probability of False Acceptance <2,5%
Sample(s) description	Socks composed by three threads 50% WO, 50% VI

Additional information of the order[2]

eurofins | Softlines & Leather

Analytical Report Nr. AR-23-YL-110329-01
Date 23-Nov-2023

Sample Information

ID	Sample Code	Client Reference[2]	Additional Information[2]
A	560-2311-00898	Ref 1985-1986 VAR 1	

SAMPLE PICTURE



Analytical Report Nr. AR-23-YL-110329-01
Date 23-Nov-2023

CONCLUSION:

TEST PROPERTY	PASS	FAIL	REMARKS
Test method for limited flame spread - Method A ISO 15025:2016			
A	X		

eurofins | Softlines & Leather

Analytical Report Nr. AR-23-YL-110329-01
Date 23-Nov-2023

RESULTS

Test method for limited flame spread - Method A
ISO 15025:2016

ID	A	Requirements:	EN ISO 11612:2015

Parameter	RESULTS	GUIDELINES
Conclusion	PASS	PASS ✓PASS
Pre-treatment	No	
Face Tested	Face	
Test temperature	21.9 ° C	
Test humidity	50 %	

Remarks: Gas used: Propane gas >95% purity
Conditioning: 24h. in indoor ambient conditions at (20±2)ºC and (65±5)%RH
Test uncertainty for after flame time and afterglow time mean values: 8,8%

Analysis Ending Date: 23/11/2023

Results

Direction	Warp			Weft			Mean value
Specimen	1	2	3	4	5	6	
After flame time (s)	0	0	0	0	0	0	0
Afterglow time (s)	0	0	0	0	0	0	0
Flaming to top or either side edge	No	No	No	No	No	No	
Loose waste	No	No	No	No	No	No	
Inflammation of the filter paper detached from waste	No	No	No	No	No	No	
Hole formation	No	No	No	No	No	No	

eurofins | Softlines & Leather

Analytical Report Nr. AR-23-YL-110329-01
Date 23-Nov-2023

Signed for and on behalf of Eurofins Textile Testing Spain:
Report electronically validated by

Axel Ferrando
Physical-Mechanical Lab Manager

EXPLANATORY NOTE

- ◆ Test not covered by ENAC accreditation scope
- ● Test is subcontracted within Eurofins group and is accredited
- ◌ Test is subcontracted within Eurofins group and is not accredited
- ■ Test is subcontracted outside Eurofins group and is accredited
- □ Test is subcontracted outside Eurofins group and is not accredited

N/A = Not Applicable

(2) Information provided by the customer. Eurofins Textile Testing Spain S.L.U is not responsible of the information supplied by the costumer and reported as section "Information provided by the costumer*"
Eurofins General Sales Terms and Conditions Applied.
Results obtained refer only to samples, products or material received in Laboratory, as described in section "Sample information" and tested in conditions shown in present report.
Test uncertainties not reported are at customer disposal , for those tests in which it is possible to evaluate the test uncertainty.
The reported expanded uncertainty is based on a standard uncertainty multiplied by a coverage factor k = 2, which for a normal distribution provides a level of confidence of approximately 95%.
Reproduction of this document is only valid if it is done completely and under the written permission. Any printed version of this document will be considered as a copy.
If you happen to have any comments, please do it by sending email to textile_spain@cpt.eurofinseu.com and referring to this report number.

End Of Report